

Volume 1, Issue 6, 2011, 242

Received: 10.11.2011 / Accepted: 11.11.2011 / Published on-line: 15.12.2011

Additions and corrections: Synthesis of poly-lysine/gold nanoparticle films and their electrocatalytic properties (Volume 1, Issue 4, 2011, 119-126)**Mariana Chirea^{1*}, Elisa M. Pereira¹, Carlos M. Pereira¹, Fernando Silva¹**

Additions and corrections. The synthesized gold nanoparticles stabilized by citrate showed a surface plasmon band at 515 nm as presented in the paper (Figure 1). In reference [9] of the paper it was mentioned that the size of these nanoparticles was 2.6 nm average diameters as determined based on the optical spectra. Transmission electron microscopy analysis of the sample shows that the average diameter size is 5.9 nm (Figure S1):




Figure S1. Transmission electron microscopy image (a) and size distribution histogram (b) of gold nanoparticles stabilized with citrate.

TEM analysis reveals the correct average diameter of the nanoparticles used in this work.

* Corresponding author e-mail address: mariana.chirea@fc.up.pt

¹ CIQ-UP L4, Faculdade de Ciências, Universidade do Porto, Rua do Campo Alegre, 687, 4169-007 Porto, Portugal